



(11) **EP 1 095 981 A1**

(12) **EUROPEAN PATENT APPLICATION**

(43) Date of publication:  
**02.05.2001 Bulletin 2001/18**

(51) Int Cl.7: **C08L 43/04, C08L 71/02**

(21) Application number: **99121261.4**

(22) Date of filing: **25.10.1999**

(84) Designated Contracting States:  
**AT BE CH CY DE DK ES FI FR GB GR IE IT LI LU  
MC NL PT SE**  
Designated Extension States:  
**AL LT LV MK RO SI**

(71) Applicant: **CEMEDINE CO., LTD.**  
**Shinagawa-ku, Tokyo (JP)**

(72) Inventors:  
• **Horie, Yasunobu, c/o Cemedine Co., Ltd.  
Tokyo (JP)**  
• **Egawa, Yoshinobu, c/o Cemedine Co., Ltd.  
Tokyo (JP)**

- **Oshima, Yuichi, c/o Cemedine Co., Ltd.  
Tokyo (JP)**
- **Hashimukai, Hideharu, c/o Cemedine Co., Ltd.  
Tokyo (JP)**
- **Wakaume, Tomokazu, c/o Cemedine Co., Ltd.  
Tokyo (JP)**
- **Aoki, Hiroshi, c/o Cemedine Co., Ltd.  
Tokyo (JP)**

(74) Representative: **Grünecker, Kinkeldey,  
Stockmair & Schwanhäusser Anwaltssozietät  
Maximilianstrasse 58  
80538 München (DE)**

(54) **Moisture curable composition**

(57) A moisture curable composition excellent in transparency, operating efficiency and storage stability, and is suitable for use as an adhesive and a sealing material is provided. The moisture curable composition produced by blending 100 parts by weight of a mixture (A) and 2 parts by weight to 300 parts by weight of amorphous powder (B). The mixture (A) comprises (1) a copolymer having reactive silicon groups which can be cross-linked by hydrolysis, whose molecular chain sub-

stantially consists of ( i ) alkylacrylate and/or alkylmethacrylate monomeric units having an alkyl group with 1 to 8 carbon atoms, and ( ii ) alkylacrylate and/or alkylmethacrylate monomeric units having an alkyl group with 10 or more carbon atoms, and (2) a polymer substantially consisting of oxyalkylene including reactive silicon groups which can be cross-linked by hydrolysis. The amorphous powder (B) has a grain diameter ranging from 0.01  $\mu\text{m}$  to 300  $\mu\text{m}$ .

**EP 1 095 981 A1**

**Description****BACKGROUND OF THE INVENTION**5     **1. Field of the Invention**

**[0001]** The present invention relates to a moisture curable composition suitable for use as an adhesive, a sealing material or the like which is required to be transparent.

10    **2. Description of Related Art**

**[0002]** Currently, a composition produced by normally blending an inorganic powder such as calcium carbonate or the like into a polymer having reactive silicon groups has been used in practice as an adhesive, a sealing material, or the like. The effect of blending the inorganic powder in this case is to give cohesive power to the polymer mainly having the reactive silicon groups, and to improve the adhesiveness on the interface with an adherend.

**[0003]** In recent years, when a transparent substrate such as glass, polycarbonate, acrylic resin or the like is adhered or sealed with an adhesive or a sealing material, the adhesive or the sealing material is also required to be transparent from the design viewpoint. However, there has been no transparent polymeric composition having reactive silicon groups which satisfies sufficient property of an adhesive or a sealing material.

**[0004]** In order to give the transparency to an adhesive and a sealing material, there are the following two methods: (1) a method without blending a filler; and (2) a method of blending an inorganic filler having a small grain diameter. However, the method (1) implies problems related to the basic properties such as the insufficient adhesiveness. The method (2) has problems that if a blended inorganic filler has a grain diameter of 0.01  $\mu\text{m}$  or more, the resultant composition can not provide a sufficient transparency, and that if the grain diameter is smaller than 0.01  $\mu\text{m}$ , it exhibits a viscosity which is abruptly increased with a small amount of the inorganic filler being added, a poor storage stability, and so on.

**[0005]** As a solvent-based adhesive which has excellent transparency without blending a filler, urethane adhesives, polyvinyl chloride adhesives and the like are placed on the market. However, when transparent adherends are adhered each other using the solvent-based adhesive, for its flowability there are formed starved areas due to air between the adherends and the adhesive, unless the adherends are adhered with a fair amount of solvent remaining therein. Such starved joints lead disadvantageously to opaque portions existing at adhering areas. The solvent included in the adhesive may also unfavorably dissolve plastics and bring about some cracks on adherends.

**OBJECT AND SUMMARY OF THE INVENTION**

**[0006]** The present inventors have devoted themselves to advance investigations so as to obtain a moisture curable composition of sufficient transparency which satisfies the basic properties of an adhesive and a sealing material, and consequently attained the present invention.


**[0007]** It is therefore an object of the present invention to provide a moisture curable composition which is excellent in transparency, operating efficiency and storage stability, and is suitable for use as an adhesive, a sealing material or the like.

**[0008]** To solve the above problem, a moisture curable composition according to the present invention is produced by blending 100 parts by weight of a mixture (A) comprising (1) a copolymer having reactive silicon groups which can be cross-linked by hydrolysis, whose molecular chain substantially consists of (i) alkylacrylate and/or alkylmethacrylate monomeric units having an alkyl group with 1 to 8 carbon atoms, and (ii) alkylacrylate and/or alkylmethacrylate monomeric units having an alkyl group with 10 or more carbon atoms, and (2) a polymer substantially consisting of oxy-alkylene including reactive silicon groups which can be cross-linked by hydrolysis, and 2 parts by weight to 300 parts by weight of amorphous powder (B) having a grain diameter ranging from 0.01  $\mu\text{m}$  to 300  $\mu\text{m}$ .

50    **DETAILED DESCRIPTION OF THE INVENTION**

**[0009]** The reactive silicon group in the mixture (A) of the present invention represents a functional group including silicon which can form cross-linking through siloxane linkage. A preferred example of the reactive silicon group will be expressed by the following general formula (I):

55



where  $R^1$  represents a substituted or unsubstituted monovalent organic group having 1 to 20 carbon atoms or a triorganosiloxy group;  $X$  represents a hydroxyl group or a heterogeneous or homogeneous hydrolyzable group;  $a$  is an integer of 0, 1 or 2;  $b$  is an integer of 0, 1, 2 or 3, provided that  $a$  is not 2 when  $b$  is 3; and  $m$  is an integer of 0 to 18.

**[0010]** The mixture (A) used in the present invention may be a polymer including silyl groups, or an acrylic polymer including silyl groups.

**[0011]** The amorphous powder (B) used in the present invention may be amorphous polymeric powder or amorphous silica. As for crystal materials such as calcium carbonate which are generally used as additives, they are apt to cause birefringence due to their optical anisotropy and lead to lower transparency due to light scattering so that they are unpreferable as additives in the present invention.

**[0012]** The polymeric powder used in the present invention is produced by emulsion polymerization, suspension polymerization or the like, and is commercially available. While (metha)acrylic acid, (metha)acrylate, vinyl acetate, ethylene and vinyl chloride are known as monomers for wide uses, the above-mentioned polymeric powder is made from a starting material of a polymer obtained by solely polymerizing one of these monomers or as the need arises by copolymerizing these monomers and one or more other monomers in consideration of particularly required properties such as adhesiveness or the like. Among monomers for wide uses as mentioned above, methylmethacrylate is particularly preferable since polymeric powder made therefrom is excellent in transparency, and weather resistance.

**[0013]** As the amorphous polymeric powder, poly(metha)acrylate powder, particularly, polymethylmethacrylate powder is preferably used. The advantages of polymethylmethacrylate powder used as the amorphous polymeric powder in the present invention are as follows: ① It exhibits low birefringence. ② It readily comes to hand because a plurality of makers place it on the market. ③ It has a refractive index close to those of polymers including silyl groups commercially available so that it readily affords transparency to the moisture curable composition of the present invention.

**[0014]** The refractive indexes of the amorphous materials and the polymers including silyl groups commercially available are shown in Table 1.

Table 1

Material	Refractive index
Polystyrene ( PS )	1.59
Polycarbonate ( PC )	1.59
Polyethylene ( HDPE )	1.54
Polyvinyl chloride ( PVC )	1.53
Polyethylene-vinyl acetate ( EVA )	1.49
Polymethylmetacrylate ( PMMA )	1.49
Polypropylene ( PP )	1.48
SILYL MAX450 *1	1.47
SILYL SAT 350 *2	1.45

\*1 SILYL MAX450: a trade name of a mixture of a polymer with a main chain of polyoxypropylene having dimethoxysilyl groups at molecular terminals, and a polymer with a main chain of a copolymer of polymethacrylate having dimethoxysilyl groups in a molecule (manufactured by Kanegafuchi Chemical Industry Co., Ltd.).

\*2 SILYL SAT350: a trade name of a polymer with a main chain of polyoxypropylene having dimethoxysilyl groups at molecular terminals (manufactured by Kanegafuchi Chemical Industry Co.).

Table 1 (continued)

Material	Refractive index
Fused silica	1.45

**[0015]** Here, the blending parts by weight of the blended amorphous powder (B) with respect to 100 parts by weight of the mixture (A) are preferably in a range of 2 parts by weight to 300 parts by weight, more preferably in a range of 5 parts by weight to 150 parts by weight, and most preferably in a range of 10 parts by weight to 75 parts by weight, particularly from viewpoints of adhesiveness and flowability. If the blending parts by weight do not reach 2 parts by weight, sufficient adhesiveness cannot be provided. On the other hand, if it exceeds 300 parts by weight, the viscosity of the resultant composition becomes extremely high to make a cured composition fragile, thus leading to a lower bonding strength.

**[0016]** If the amorphous powder (B) has a grain diameter smaller than 0.01  $\mu\text{m}$ , it is difficult to obtain monodispersed dry powder. On the contrary, if the grain diameter exceeds 300  $\mu\text{m}$ , the thickness of an adhesive layer cannot be reduced, thereby causing a problem such as a surface devoid of smoothness or the like. Thus, the grain diameter of the amorphous powder (B) is preferably in a range of 0.01  $\mu\text{m}$  to 300  $\mu\text{m}$ , more preferably in a range of 0.1  $\mu\text{m}$  to 100  $\mu\text{m}$ , and most preferably in a range of 1  $\mu\text{m}$  to 30  $\mu\text{m}$ .

**[0017]** To further improve the transparency of the moisture curable composition of the present invention, it is preferable to mate the refractive index of the mixture (A), which is a liquid phase and composed of the copolymer (1) having reactive silicon groups and the oxyalkylene polymer (2), as close as possible with the refractive index of the amorphous powder (B), which is a solid phase. The difference of the refractive indexes between the liquid phase and the solid phase is preferably in a range of 0.03 to 0.1, more preferably 0.02 to 0.05, and most preferably in a range of 0.01 to 0.02 particularly from a viewpoint of transparency.

**[0018]** For mating the refractive index of the mixture (A), which is a liquid phase, with that of the amorphous powder (B), which is a solid phase, the mixture (A), may be blended with a required amount of a compatible material such as a petroleum resin. Alternatively, for mating the refractive index of the solid phase with that of the liquid phase, the blending ratio of monomers in the amorphous powder (B), which is a solid phase, may be changed fittingly.

**[0019]** As a method of mating the refractive index of the amorphous powder (B), which is a solid phase, with the refractive index of the mixture (A), which is a liquid phase, there is (1) a method of approaching the refractive index of the mixture (A) to the refractive index of the amorphous powder (B); and (2) a method of approaching the refractive index of the amorphous powder (B) to the refractive index of the mixture (A).

**[0020]** As for the method (1), when the solid phase is polymeric powder since the refractive index of the mixture (A) which is a liquid phase is generally lower than that of the solid phase, the refractive index of the mixture (A) can be increased by heating a material having a refractive index higher than that of the mixture (A) (approximately 1.46 to 1.48) to melt it into a reactive polymer. Examples of the material having a refractive index higher than that of the mixture (A) include an epoxy resin (for example, Epicoat 828 (bisphenol A having a refractive index of 1.57, manufactured by Yuka Shell Epoxy Co., Ltd.); a petroleum resin (for example, FTR6100 (a copolymer of C5 and C9) having a refractive index of 1.56, manufactured by Mitsui Chemicals Inc.); and a terpene phenol resin (for example, Polyester T145 having a refractive index of 1.59, manufactured by Yasuhara Chemicals Co., Ltd.).

**[0021]** As for the method (2), for increasing the refractive index of the amorphous powder (B), there is a method of copolymerizing monomers, for example, vinyl chloride (having a refractive index of 1.53 (polymer)), acrylonitrile (having a refractive index of 1.52 (polymer)), or the like with (metha)acrylate monomers used in the present invention. For reducing the refractive index of the powder (B), there is a method of copolymerizing monomers, for example, lauryl-methacrylate (having a refractive index of 1.44 (monomer)), allylmethacrylate (having a refractive index of 1.44 (monomer)), 2(2-ethoxyethoxy)ethylacrylate (having a refractive index of 1.43 (monomer)), or the like with (metha)acrylate monomers used in the present invention.

**[0022]** The moisture curable composition of the present invention may become a non-solvent-based adhesive or a non-solvent-based sealing material which is free from the above-mentioned disadvantages of a solvent-based adhesive. There has conventionally unknown such an adhesive or a sealing material possessing both of adhesiveness and transparency. Using poly(metha)acrylate powder as amorphous polymeric powder, the moisture curable composition of the present invention becomes excellent in chemical resistance such as acid resistance, and exhibits advantages such as a specific gravity reducing effect. Conventional inorganic powder such as calcium carbonate is inferior in acid resistance and exhibits disadvantages such as a specific gravity increasing effect.

**[0023]** When plastic materials are adhered with the moisture curable composition of the present invention, an effect can be seen in an improved adhesiveness which cannot be provided by a conventional composition using calcium carbonate as a filler.

**[0024]** There may be added to the moisture curable composition of the present invention a variety of additives which

do not spoil the transparency thereof. For example, silica fine powder may be added as inorganic powder. Also, a tackifier may be added as required. It is further possible to add a liquid material which does not dissolve the amorphous powder if it is required to adjust the viscosity.

## 5      EXAMPLES AND COMPARATIVE EXAMPLES

**[0025]** In the following, the present invention will be described in more specific manner with reference to several examples.

10      (Examples 1 - 4 and Comparative Examples 1 - 2)

**[0026]** Respective components were placed in a planetary mixer with blending ratios shown in Table 2, mixed for one hour at 100 °C and 10 mmHg, and then cooled to 20 °C. A curing catalyst and a tackifier were added to the mixed components, and all the components were vacuum mixed for ten minutes to obtain room temperature curable compositions for the respective blending ratios.

15      **[0027]** The blending amount of FTR8100 is determined in the following manner. First, FTR8100 serving as a refractive index adjusting agent is heated and melted into a polymer having a reactive silicon group at a proper ratio, and the refractive index of the melt is measured by an Abbe refractometer at 20 °C. The relationship between the blending ratio of FTR8100 and the refractive index of the resultant mixture is plotted on an X-Y coordinate plane. The blending amount of FTR8100 whose refractive index is in accord with that of powder used as a main filler is the detected blending amount.

20      **[0028]** Further, the respective room temperature curable compositions were evaluated with respect to storage stability, transparency and bonding strength, and the results were listed in a lower part of Table 2.

Table 2

	REFRACTIVE INDEX	EXAMPLE No.				COMPARATIVE EXAMPLE No.	
		1	2	3	4	1	2
BLENDING AMOUNT (PARTS BY WEIGHT)	SILYL MAX450	100	100	100	-	100	100
	SILYL SAT350	-	-	-	100	-	-
	MR13G	50	40	40	-	-	-
	Fuselex E2	-	5	-	40	-	-
	AEROSIL 200	-	-	5	-	10	-
PROPERTY EVALUATION	FTR8100	17	17	17	-	-	-
	Dibutyltin dilaurate	2	2	2	2	2	2
	SH6020	4	4	4	4	4	4
	Storage Stability *1	⊙	⊙	⊙	○	×	⊙
	Transparency *2	⊙	○	⊙	⊙	○	⊙
	Bonding Strength *3 (N/cm <sup>2</sup> )	380	420	450	150	210	100

[0029] The components in Table 2 are as follows:

SILYL MAX450: a trade name of a mixture of a polymer with a main chain of polyoxypropylene having dimethoxysilyl groups at molecular terminals, and a polymer with a main chain of a copolymer of polymethacrylate having dimethoxysilyl groups in a molecule (manufactured by Kanegafuchi Chemical Industry Co., Ltd.).

SILYL SAT350: a trade name of a polymer with a main chain of polyoxypropylene having dimethoxysilyl groups at molecular terminals (manufactured by Kanegafuchi Chemical Industry Co., Ltd.).

MR13G: a trade name of methacrylate polymeric powder (having an average grain diameter of approximately 1 µm) (manufactured by Soken Chemicals Co., Ltd.).

FTR8100: a trade name of a petroleum resin having a copolymer of C5 and C9 (manufactured by Mitsui Chemicals Inc.).

Fuselex E2: a trade name of amorphous silica (having an average grain diameter of approximately 5 µm) (manufactured by Tatsumori Co., Ltd.).

AEROSIL 200: a trade name of silica fine powder (manufactured by Nippon AEROSIL Co., Ltd.).

Dibutyltindilaurate: a curing catalyst.

SH6020: a trade name of a silane coupling agent (γ - (2-aminoethyl) aminopropyltrimethoxysilane) (manufactured by Toray Dow Corning Silicone Co., Ltd.).

[0030] The respective property evaluations in Table 2 were conducted in the following manner.

Storage Stability (\*1): The ratio of the viscosity after the lapse of seven days at 50 °C to the initial viscosity was evaluated as follows: ⊙: more than 1.2 times; ○: 1.2 - 1.3 times; and ×: less than 1.3 times.

Transparency (\*2): The adhesive was spread between two acrylic plates of 2 mm in thickness using a spacer of 3 mm, and the transparency was observed and evaluated as follows: ⊙: colorless and transparent; ○: colorless but slightly opaque; and ×: opaque.

Bonding Strength (\*3): The adhesive was applied in a thickness of 200 µm over an adhering area of 25 x 25 mm of two acrylic plates (2x25x100 mm) respectively, and the acrylic plates were adhered to each other after the lapse of an open time (a time of exposure to atmospheric moisture) of three minutes. The adhesive was cured for seven days at 20 °C, and its bonding strength was measured at a tensile speed of 50 mm/minute.

[0031] As is apparent from Table 2, Example 1 exhibits particularly good transparency and a high bonding strength because of the use of MR13G as a transparent filler. Example 2 exhibits slightly degraded transparency since a combination of MR13G and Fuselex E2 is used as a transparent filler so that the refractive index of Fuselex E2 should be mated with the refractive index of MR13G.

[0032] Example 3 exhibits good transparency since Fuselex E2 in Example 2 is replaced with AEROSIL 200 which has a finer grain diameter than Fuselex E2. In addition, the bonding strength is also increased since the cohesive force of the cured composition is higher probably by virtue of the added AEROSIL.

[0033] In Example 4, SILYL SAT350 is used as a polymer having reactive silicon groups, which is a liquid phase, since Fuselex E2 which has a low refractive index is used as a transparent filler. Although the composition of Example 4 exhibits a lower bonding strength as compared with Examples 1-3, Example 4 is listed in Table 2 as a blending example of a sealing material which only needs a lower bonding strength than an adhesive.

[0034] In Comparative Example 1 in which AEROSIL 200 (silica fine powder) was only added, while the transparency and the bonding strength were good, the storage stability was significantly lower. Also, in Comparative Example 2 where no filler including inorganic powder was added, it was found that while the storage stability and the transparency were excellent, the bonding strength was significantly lower.

[0035] As described above, the moisture curable composition of the present invention is excellent in transparency, operating efficiency and storage stability, and is suitable for use as an adhesive and a sealing material.

[0036] Obviously, various minor changes and modifications of the present invention are possible in the light of the above teaching. It is therefore to be understood that within the scope of appended claims the invention may be practiced otherwise than as specifically described.

## Claims

1. A moisture curable composition produced by blending:

- 100 parts by weight of a mixture (A) comprising:

(1) a copolymer having reactive silicon groups which can be cross-linked by hydrolysis, whose molecular chain substantially consists of:

( i ) alkyacrylate and/or alkylmethacrylate monomeric units having an alkyl group with 1 to 8 carbon atoms; and

(ii) alkyacrylate and/or alkylmethacrylate monomeric units having an alkyl group with 10 or more carbon atoms; and

(2) a polymer substantially consisting of oxyalkylene including reactive silicon groups which can be cross-linked by hydrolysis; and

- 2 parts by weight to 300 parts by weight of amorphous powder (B) having a grain diameter ranging from 0.01  $\mu\text{m}$  to 300  $\mu\text{m}$ .

2. A moisture curable composition according to claim 1, wherein said mixture (A) has a refractive index mated with a refractive index of said amorphous powder (B).
3. A moisture curable composition according to claim 1 or 2, wherein said amorphous powder (B) is amorphous polymeric powder or amorphous silica.
4. A moisture curable composition according to claim 3, wherein said amorphous polymeric powder is a polymer obtained by polymerizing solely a monomer selected from a group consisting of (metha) acrylate, vinyl acetate, ethylene, and vinyl chloride or by copolymerizing said monomer with one or more of vinyl monomers.
5. A moisture curable composition according to claim 4, wherein said amorphous polymeric powder is polymethyl methacrylate powder.
6. A moisture curable composition according to any one of claims 1 to 5, wherein said mixture (A) is a polymer including silyl groups.
7. A moisture curable composition according to claim 6, wherein said polymer is an acrylic polymer including silyl groups.



European Patent  
Office

## EUROPEAN SEARCH REPORT

Application Number  
EP 99 12 1261

DOCUMENTS CONSIDERED TO BE RELEVANT			
Category	Citation of document with indication, where appropriate, of relevant passages	Relevant to claim	CLASSIFICATION OF THE APPLICATION (Int.Cl.7)
X	EP 0 339 666 A (KANEKAFUCHI CHEMICAL IND) 2 November 1989 (1989-11-02) * page 7, line 32 - line 36; example 7 *	1	C08L43/04 C08L71/02
X	EP 0 525 769 A (KANEKAFUCHI CHEMICAL IND) 3 February 1993 (1993-02-03) * page 6, line 38 - line 44 *	1	
X	EP 0 541 074 A (SUNRISE MEISEI CORP) 12 May 1993 (1993-05-12) * page 4, line 25: claims 1,7,9: examples *	1	
			TECHNICAL FIELDS SEARCHED (Int.Cl.7)
			C08L
The present search report has been drawn up for all claims			
Place of search THE HAGUE		Date of completion of the search 29 May 2000	Examiner Schueler, D
CATEGORY OF CITED DOCUMENTS X particularly relevant if taken alone Y particularly relevant if combined with another document of the same category A technological background O non-written disclosure P intermediate document T theory or principle underlying the invention E earlier patent document but published on, or after the filing date D document cited in the application L document cited for other reasons & member of the same patent family, corresponding document			

EPO FORM 1503 03/82 (Prelim)

**ANNEX TO THE EUROPEAN SEARCH REPORT  
ON EUROPEAN PATENT APPLICATION NO.**

EP 99 12 1261

This annex lists the patent family members relating to the patent documents cited in the above-mentioned European search report. The members are as contained in the European Patent Office EDP file on  
The European Patent Office is in no way liable for these particulars which are merely given for the purpose of information.

29-05-2000

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
EP 0339666 A	02-11-1989	JP 1275648 A	06-11-1989
		JP 2634630 B	30-07-1997
		CA 1336792 A	22-08-1995
		DE 68921664 D	20-04-1995
		DE 68921664 T	07-09-1995
		ES 2072272 T	16-07-1995
		US 5030691 A	09-07-1991
EP 0525769 A	03-02-1993	JP 5032934 A	09-02-1993
		JP 2916653 B	05-07-1999
		JP 5065454 A	19-03-1993
		JP 5086325 A	06-04-1993
		DE 69230050 D	04-11-1999
		DE 69230050 T	23-03-2000
		ES 2137168 T	16-12-1999
EP 0541074 A	12-05-1993	JP 5125271 A	21-05-1993

EPC FORM P0459

For more details about this annex : see Official Journal of the European Patent Office. No. 12/82